IRON 15MY



Film Specification

Elite Films

PROPERTY		Thickness	15µ	TEST METHOD
TENSILE STRENGTH	MD	UP TO	52	ASTM D 882
(Mpa)	TD	UP TO	27	ASTM D 882
ELONGATION	MD	UP TO	360	ASTM D 882
(%)	TD	UP TO	500	ASTM D 882
TEAR STRENGTH	MD	UP TO	125	ASTM D 1922
(elmendorf) (gm)	TD	UP TO	370	ASTM D 1922
IMPACT STRENGTH (drop dart) (gm)		UP TO	90	ASTM D 1709
HAZE (%)		LESS THAN	1	ASTM D 1003
GLOSS (45 deg. Angle) (%)		UP TO	90	ASTM D 2457
STRETCH LEVEL (%)			100	HIGHLIGHT TESTER

Paper Core Specification

DIMENSION	TOLERANCE
LENGTH (mm)	± 2.0
THICKNESS (mm)	± 0.30

Film Dimension Specification

DIMENSION	TOLERANCE
FILM WIDTH (mm)	± 2.0
FILM THICKNESS (µm)	± 1.5

Tutti i film BI&ESSE sono atossici e riciclabili al 100%

Tolleranze: Lunghezza ± 2.0 mm - Larghezza ± 2.0 mm - Spessore ± 1.5 µm
I valori riportati sono il risultato di prove standardizzate, sono forniti a titolo indicativo atti a facilitare la scelta l'impiego per ogni settore di possibile utilizzo e non costituiscono quindi garanzia. Raccomandiamo all'acquirente di controllare l'idoneità e l'adeguatezza per le applicazioni che intende fare. Bi&esse espressamente declina qualsiasi responsabilità in caso di danni diretti o indiretti derivanti dall'utilizzo inappropriato dei prodotti.

